



November 2017

**RESEARCH PROJECT TITLE**

Impacts of Internally Cured Concrete  
Paving on Contraction Joint Spacing

**SPONSORS**

Iowa Highway Research Board  
(IHRB Project TR-676)  
Iowa Department of Transportation  
(InTrans Project 14-499)

**PRINCIPAL INVESTIGATOR**

Peter Taylor, Director  
National Concrete Pavement Technology  
Center, Iowa State University  
515-294-9333 / ptaylor@iastate.edu  
([orcid.org/0000-0002-4030-1727](https://orcid.org/0000-0002-4030-1727))

**CO-PRINCIPAL INVESTIGATOR**

Halil Ceylan, Director  
Program for Sustainable Pavement  
Engineering and Research (ProSPER),  
Institute for Transportation, Iowa State  
University  
([orcid.org/0000-0003-1133-0366](https://orcid.org/0000-0003-1133-0366))

**MORE INFORMATION**

[www.cptechcenter.org](http://www.cptechcenter.org)

**National CP Tech Center  
Iowa State University  
2711 S. Loop Drive, Suite 4700  
Ames, IA 50010-8664  
515-294-3230**

The mission of the National Concrete Pavement Technology Center is to unite key transportation stakeholders around the central goal of advancing concrete pavement technology through research, tech transfer, and technology implementation.

The sponsors of this research are not responsible for the accuracy of the information presented herein. The conclusions expressed in this publication are not necessarily those of the sponsors.

# Impacts of Internal Curing on the Performance of Concrete Materials in the Laboratory and the Field

tech transfer summary

This research aimed to assess whether joint spacings could be increased in slabs containing lightweight fine aggregate (LWFA) as a source of internal curing.

## Objective

The objective of this project was to investigate the effects of internal curing on the performance of practical concrete mixtures designed for the construction of jointed plain concrete pavements (JPCPs) in Iowa.

## Background

Concrete curing involves techniques and methods to maintain the moisture and temperature of fresh concrete within desired ranges at early ages, which allows concrete to develop strength and durability. Various curing regimes, including external wet curing, insulation membrane curing, and internal curing, can be used for different applications and design characteristics.

Internal curing is designed to provide water reservoirs inside the concrete that aid curing without affecting the water-to-cementitious materials (w/cm) ratio of the mixture. Lightweight aggregates (LWAs) are commonly employed in the US to achieve internal curing.

Internally cured (IC) concrete has several advantages over conventionally cured concrete:

- Improved hydration in terms of uniform moisture distribution
- Reduced autogenous, plastic, and drying shrinkage, reducing the likelihood of shrinkage cracking
- Reduced concrete permeability and enhanced resistance to sulfate attack
- Improved strength and permeability at the interface transition zone (ITZ)
- Reduced modulus of elasticity (MoE) and enhanced residual stress relaxation due to the presence of LWAs
- Reduced moisture gradient along the concrete section, reducing warping in pavements
- Reduced coefficient of thermal expansion (CTE) and thermal conductivity, reducing temperature gradients throughout the concrete and reducing curling in pavements



